

種類	強度等級				含水率				
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図	
杉正角	E50	518	4.4		15%以下	10,986	93.0		
	E70	4,196	35.5			635	5.4		
	E90	4,646	39.3			152	1.3		
	E110	2,121	18.0			31	0.3		
	E130	305	2.6			合計	11,804		100.0
	E150	18	0.2						
	合計	11,804	100.0						
杉平角	E50	96	4.2		15%以下	2,211	96.2		
	E70	702	30.5			65	2.9		
	E90	1,010	44.0			17	0.8		
	E110	435	18.9			2	0.1		
	E130	47	2.1			合計	2,295		100.0
	E150	5	0.3						
	合計	2,295	100.0						
桧正角	E50	30	0.3		15%以下	11,247	88.0		
	E70	398	3.2			1,470	11.6		
	E90	2,632	20.6			41	0.4		
	E110	5,677	44.4			0	-		
	E130	3,402	26.6			合計	12,758		100.0
	E150	619	4.9						
	合計	12,758	100.0						