

種類	強度等級				含水率				
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図	
杉正角	E50	4,688	4.8		15%以下	77,956	78.2		
	E70	32,602	32.7			16,257	16.3		
	E90	40,558	40.6			5,253	5.3		
	E110	18,332	18.4			113	0.2		
	E130	3,055	3.1			合計	99,579		100.0
	E150	344	0.4						
	合計	99,579	100.0						
杉平角	E50	733	5.4		15%以下	11,703	85.1		
	E70	4,504	32.7			1,284	9.4		
	E90	6,104	44.4			576	4.2		
	E110	2,047	14.8			177	1.3		
	E130	318	2.4			合計	13,740		100.0
	E150	34	0.3						
	合計	13,740	100.0						
桧正角	E50	125	0.2		15%以下	77,795	78.2		
	E70	1,544	1.6			20,254	20.5		
	E90	17,466	17.6			1,105	1.2		
	E110	45,772	46.0			4	0.1		
	E130	29,160	29.4			合計	99,158		100.0
	E150	5,091	5.2						
	合計	99,158	100.0						