

種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50	872	5.0		15%以下	12,433	69.7	
	E70	4,271	24.1		15~20%	3,343	18.8	
	E90	7,540	42.1		20~25%	1,924	10.9	
	E110	4,196	23.6		25%以上	90	0.6	
	E130	817	4.6		合計	17,790	100.0	
	E150	94	0.6					
	合計	17,790	100.0					
杉平角	E50	0	---		15%以下	0	---	
	E70	0	---		15~20%	0	---	
	E90	0	---		20~25%	0	---	
	E110	0	---		25%以上	0	---	
	E130	0	---		合計	0	0.0	
	E150	0	---					
	合計	0	0.0					
桧正角	E50	13	0.1		15%以下	21,211	76.6	
	E70	252	1.0		15~20%	5,992	21.7	
	E90	3,504	12.7		20~25%	435	1.6	
	E110	12,053	43.3		25%以上	3	0.1	
	E130	9,718	35.2		合計	27,641	100.0	
	E150	2,101	7.7					
	合計	27,641	100.0					