







種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50	3,946	3.5		15%以下	86,840	80.2	
	E70	28,257	25.1		15~20%	21,034	19.4	
	E90	49,947	44.4		20~25%	408	0.4	
	E110	25,099	22.3		25%以上	0	0.0	
	E130	4,827	4.3		合計	108,282	100.0	
	E150	462	0.4					
	合計	112,538	100.0					
杉平角	E50	297	3.6		15%以下	6,707	88.5	
	E70	2342	28.0		15~20%	874	11.5	
	E90	3,903	46.7		20~25%	0	0.0	
	E110	1586	19.0		25%以上	0	0.0	
	E130	210	2.5		合計	7,581	100.0	
	E150	13	0.2					
	合計	8,351	100.0					
桧正角	E50	1,016	0.4		15%以下	217,418	93.2	
	E70	2,652	1.1		15~20%	15,813	6.7	
	E90	29,253	12.5		20~25%	4	0.1	
	E110	99,992	42.7		25%以上	0	0.0	
	E130	81,620	34.8		合計	233,235	100.0	
	E150	19,689	8.5					
	合計	234,222	100.0					