





種類	強度等級				含水率			
	強度等級	本数	比率(%)	強度等級分布図	含水率	本数	比率(%)	含水率分布図
杉正角	E50 (6.9以下)	2,134	18.7		15%以下	7,916	75.7	
	E70 (7.0~8.9)	5,120	45.1		15~20%	2,509	23.9	
	E90 (9.0~10.9)	3,257	28.7		20~25%	41	0.4	
	E110 (11.0~12.9)	783	6.8		25%以上	0	0.0	
	E130 (13.0~14.9)	65	0.6		合計	10,466	100.0	
	E150 (15.0以上)	2	0.1					
	合計	11,361	100.0					
杉平角	E50 (6.9以下)	193	28.0		15%以下	515	88.5	
	E70 (7.0~8.9)	322	46.5		15~20%	67	11.5	
	E90 (9.0~10.9)	147	21.2		20~25%	0	0.0	
	E110 (11.0~12.9)	28	4.1		25%以上	0	0.0	
	E130 (13.0~14.9)	1	0.2		合計	582	100.0	
	E150 (15.0以上)	0	0.0					
	合計	691	100.0					
桧正角	E50 (6.9以下)	198	0.9		15%以下	21,355	92.6	
	E70 (7.0~8.9)	1,414	6.0		15~20%	1,701	7.4	
	E90 (9.0~10.9)	8,258	35.5		20~25%	0	0.0	
	E110 (11.0~12.9)	10,400	44.8		25%以上	0	0.0	
	E130 (13.0~14.9)	2,822	12.1		合計	23,056	100.0	
	E150 (15.0以上)	156	0.7					
	合計	23,248	100.0					